

導電發泡, LCX 系列產品物性表
Conductive Foam, LCX SERIES PHYSICAL PROPERTIES

項目 Items 品名 Articles	硬度 Hardness <i>ASTM D2240</i> SHORE C SHORE 00		延伸率 Elongation Ratio <i>ASTM D412</i> (%) ↑	抗張強度 Tensile Strength <i>ASTM D412</i> (kPa) ↑	撕裂強度 Tear Strength <i>ASTM D624</i> (kN/m) ↑	25%壓縮應力 Compression Strength 25% <i>ASTM D1056</i> (kPa) ↑	25%壓縮變型 Compression Set 25% <i>ASTM D1056</i> (%) ↓	密度 Density <i>ASTM D3575</i> (kg/m ³)	表面阻抗 Surface Resistivity <i>ASTM D257</i> Ω	規格 Standard Size (mm)	備註 Note	
LCX-200#2	24±4	40~60	49	320	1.4	70	8.0	50±5	10 ⁴ ~10 ⁶	1000*2000*80		
LCX-150	45±5	60~80	44	410	1.8	110	11.2	60±5	10 ⁴ ~10 ⁶	1000*1000*75		
2018.7.4												

本表所提供之數值皆為代表值，並非保證值。
All given data should be considered as a guide, but can not be regarded as an engagement from our side.