



勝特力材料 886-3-5753170
 勝特力电子(上海) 86-21-54151736
 勝特力电子(深圳) 86-755-83298787
[Http://www.100y.com.tw](http://www.100y.com.tw)

Super 88 Vinyl Electrical Tape

Data Sheet



LISTED
539H Insulating Tape



LR48769

Product Description

Scotch® Super 88 Vinyl Electrical Tape is a premium grade, 8.5 mil thick, all-weather vinyl insulating tape. It is designed to perform continuously in ambient temperatures up to 105°C (220°F). The tape is conformable for cold weather application down to -18°C (0°F). It has excellent resistance to abrasion, moisture, alkalis, acids, corrosion and varying weather conditions (including ultraviolet exposure). The combination of elastic backing and aggressive adhesive provides moisture-tight electrical and mechanical protection with minimum bulk. Super 88 is an Underwriters' Laboratories Listed and Canadian Standards Association Certified "Insulating Tape".

- UL Listed; UL 510 Standard "Insulating Tape" (product category OANZ), File E129200
- CSA Certification; Standard C22.2 No.197-M1983 "PVC Insulating Tape," File LR 48769
- Polyvinyl chloride (PVC) backing.
- Pressure-sensitive rubber based adhesive.
- Compatible with solid dielectric cable insulations.
- Compatible with rubber and synthetic splicing compounds, as well as epoxy and polyurethane resins.
- Inhibits corrosion of electrical conductors.
- For indoor or outdoor applications.
- Complies with property requirements of Federal Specification MIL-I-24391

Applications

- Primary electrical insulation for all wire and cable splices rated up to 600 volts and 105°C (220°F).
- Primary electrical insulation for 600 volt bus applications, and protective jacketing for low and high voltage bus.
- Protective jacketing for high voltage cable splices and repairs.
- Harnessing of wires and cables.

Typical Data / Physical Properties

Temperature Rating:

UL 510 80°C (176°F)

CSA

C22.2 No. 197-M1983

Handling -18°C (0°F)

Continuous Operation 105°C (220°F)

Color

Black

Thickness

ASTM D1000 8.5 mils

Adhesion to Steel

ASTM D1000

22°C (72°F) 25 oz./in.

-18°C (0°F) 60 oz./in.

Adhesion to Backing

ASTM D1000

22°C (72°F) 25 oz./in.

-18°C (0°F) 60 oz./in.

Breaking Strength

ASTM D1000

22°C (72°F) 20 lbs./in.

Ultimate Elongation

ASTM D1000

22°C (72°F) 250%

-18°C (0°F) 100%

Flammability (Maximum)

UL 510

1 sec.

ASTM D1000

4 sec.

Accelerated Aging

ASTM D1000

80%

Flagging

ASTM D1000

<0.1 inch

Telescoping

24 Hours @ 50°C (120°F)

<0.1 inch

Electrical Properties:

Voltage Rating

UL 510

600V

Dielectric Breakdown

ASTM D1000

Standard Condition

10000 volts

High Humidity Condition

90% of Standard

Insulation Resistance

ASTM D1000

>1 x10⁶ megohms

(High Humidity Method)

Note: These are typical values and should not be used for specification purposes.

Specification

Product

The tape is based on polyvinyl chloride (PVC) and/or its copolymers and has a rubber-based, pressure-sensitive adhesive. The tape shall be 8.5 mils thick, and be UL Listed and marked per UL Standard 510 as "Flame Retardant, Cold and Weather Resistant." The tape must be applicable at temperatures ranging from 0°F through 100°F (-18°C through 38°C) without loss of physical properties. The tape shall be classified for use in both indoor and outdoor environments. The tape shall be compatible with synthetic cable insulations, jackets and splicing compounds. The tape will remain stable and will not telescope more than 0.1 inches when maintained at temperatures below 120°F (50°C).

Engineering/Architectural

Specification

Primary electrical insulation (branch wiring in wet or dry locations): All splices for 600 volt wire rated 105°C (220°F) and below shall be insulated with a minimum of two half-lapped layers of Scotch® Super 88 Vinyl Electrical Tape. All connectors having irregular surfaces shall be padded with

Scotchfil™ Electrical Insulation Putty or 3M 130C Rubber Splicing Tape prior to insulating with Scotch Super 88 Vinyl Electrical Tape.

Mechanical protection (outer jacketing)

All rubber and thermoplastic insulating high voltage power cable tape splices and repairs shall be overwrapped with at least two half-lapped layers of 3M Super 88 Vinyl Electrical Tape.

Installation Techniques

The tape shall be applied in half-lapped layers with sufficient tension to produce a uniform wind (for most applications this tension will reduce the tape's width to approximately 5/8 of its original width). On pigtail splices, the tape shall be wrapped beyond the end of the wires and then folded back, leaving a protective cushion to resist cut-through. Wrap tape up-hill, taping from a smaller diameter surface to a larger diameter surface. Apply the tape with no tension on the last wrap to prevent flagging.

Shelf Life

Scotch® Super 88 Vinyl Electrical Tape has a 5 year shelf life (from date of manufacture) when stored under the following recommended storage conditions. Store behind present stock in a clean dry place at a temperature of 70°F (21°C) and 40-50% relative humidity.

Availability

Scotch® Super 88 Vinyl Electrical Tape is available from your local 3M authorized distributor in the following standard roll sizes:

3/4 in. x 66 ft.

3/4 in. x 44 ft.

3/4 in. x 36 yd.

1-1/2 in. x 44 ft.

1-1/2 in. x 36 yd.

Other lengths and widths are available by special request.

3M, Scotch and Scotchfil are trademarks of 3M.

Electrical Products Division

6801 River Place Blvd.
Austin, TX 78726-9000
www.3M.com/elpd

Litho in USA

©3M IPC 2001 78-8124-4857-5-C

3M

勝特力材料 886-3-5753170
勝特力电子(上海) 86-21-54151736
勝特力电子(深圳) 86-755-83298787
[Http://www.100y.com.tw](http://www.100y.com.tw)