



勝特力材料 886-3-5753170
 勝特力电子(上海) 86-21-54151736
 勝特力电子(深圳) 86-755-83298787
[Http://www.100y.com.tw](http://www.100y.com.tw)

- Specific gravity of solder.....8.40
- Tin content%.....62.83
- Flux contents.....1.80
- Chlorine content in flux.....0.69
- Acid number of flux.....164~166
- Softing point of flux.....72~73°C
- Insulation resistance normal temp... 10×10^{12}
- Insulation resistance after humidifying
- For 72 hour at 40°C 90%RH..... $1.6 \times 10^{14} \sim 1.0 \times 10^{12}$
- Insulation resisitance after humidifying
- For 250hours at 40°C 90%RH..... $1.5 \sim 7.0 \times 10^{11}$
- Spreadability89
- Corrosion.....normal